

FILTER MEDIA



Characteristics	Unit	Specification	Test Method
Thickness	mm	0.6 +/- 0.2	JIS L 1096
Weight	g/sqm	72 +/- 7	JIS L 1096
Tensile Strength	N/5cm	MD	60 or more
		CD	25 or more
Air Permeability	cm ³ /cm ² /sec	220 +/- 60	JIS L 1096
Antibacterial Performance		(2 or more)	JIS L 1902
Fungal Resistance		(1 or more)	JIS Z 2911



Headquarters

4750 NE Dawson Creek Dr.
 Hillsboro, Oregon 97124
 Phone: (503) 693-1070 Fax: (503) 648-1185
www.dynic.com